

Result of samples analysis Oct 2010 by A-BAN (BANKO, AMRC) & ABEVA

sampling date	number	site1	site2	sample1	sample2	asbestos type	concentration	analysis method
Sep 15 2010	1	Belgium	neary by Eternit factory, roof of a house	roofing material	solid	chrysotile	10-12%	FE-SEM (field-emission scanned electron microscopy) and EDS (energy dispersive spectroscopy)
						crocidolite	4-5%	
	2	Belgium	Eternit's sports center playground	pipe?	solid	chrysotile	20%	
	3	Belgium	Eternit's sports center playground	roofing material	solid	chrysotile	6-7%	
	4	Belgium	Eternit's sports center playground	roofing material	solid	chrysotile	8-9%	
	5	Belgium	backyard of Eric's house site nearby Eternit's sports center	plain plate	solid	chrysotile	20-22%	
	6	Belgium	backyard of Eric's house site nearby Eternit's sports center	pipe	solid	chrysotile	20-21%	
			backyard of Eric's house site nearby Eternit's sports center			crocidolite	20%	
7	Belgium	backyard of Eric's house site nearby Eternit's sports center	sprayed	solid	chrysotile	5-6%		
					crocidolite	4-5%		